

U.S. PTO Customer No. 25280

Case# 5392

Claim Amendments

1. (previously amended) An antimicrobial sol-gel film comprising at least one silver-containing inorganic antimicrobial agent, wherein said film exhibits a log kill rate for *Klebsiella pneumoniae* of at least 0.5 as measured under a modified plate contact method, and wherein said film is capable of adherence to a hard surface substrate at a temperature of between 100°C and 800°C.
2. (original) The antimicrobial sol-gel film of Claim 1 wherein said film exhibits a log kill rate for *Klebsiella pneumoniae* of at least 1.0.
3. (original) The antimicrobial sol-gel film of Claim 2 wherein said film exhibits a log kill rate for *Klebsiella pneumoniae* of at least 2.0.
4. (original) The antimicrobial sol-gel film of Claim 3 wherein said film exhibits a log kill rate for *Klebsiella pneumoniae* of at least 3.0.
5. (original) The antimicrobial sol-gel film of Claim 4 wherein said film exhibits a log kill rate or *Klebsiella pneumoniae* of at least 3.5.

Claims 6-15 (cancelled)

16. (currently amended) A hard surface substrate to which a sol-gel film has been applied over at least a portion of the surface thereof at a temperature of between 100°C and 800°C, wherein the sol-gel film contains at least one silver-containing inorganic antimicrobial agent,

U.S. PTO Customer No. 25280

Case# 5392

and wherein said film-coated hard surface substrate exhibits a log kill rate for *Klebsiella pneumoniae* of at least 0.5, as measured under a modified plate contact method, at said portion to which said sol-gel film has been applied.

17. (currently amended) The hard surface substrate of Claim 16 wherein said film-coated hard surface substrate exhibits a log kill rate for *Klebsiella pneumoniae* of at least 1.0 at said portion to which said sol-gel film has been applied.

18. (currently amended) The hard surface substrate of Claim 16 wherein said film-coated hard surface substrate exhibits a log kill rate for *Klebsiella pneumoniae* of at least 2.0 at said portion to which said sol-gel film has been applied.

19. (currently amended) The hard surface substrate of Claim 16 wherein said film-coated hard surface substrate exhibits a log kill rate for *Klebsiella pneumoniae* of at least 3.0 at said portion to which said sol-gel film has been applied.

20. (currently amended) The hard surface substrate of Claim 16 wherein said film-coated hard surface substrate exhibits a log kill rate for *Klebsiella pneumoniae* of at least 3.5 at said portion to which said sol-gel film has been applied.

21. (currently amended) The hard surface substrate of Claim 18 exhibiting the same log kill rate after said film-coated substrate has been immersed in a heated caustic bath, having a pH level of at least 12, for 48 hours.

U.S. PTO Customer No. 25280

Case# 5392

22. (currently amended) The hard surface substrate of Claim 19 exhibiting the same log kill rate after said film-coated substrate has been immersed in a heated caustic bath, having a pH level of at least 12, for 48 hours.

23. (currently amended) The hard surface substrate of Claim 20 exhibiting the same log kill rate after said film-coated substrate has been immersed in a heated caustic bath, having a pH level of at least 12, for 48 hours.

24. (previously added) The antimicrobial sol-gel film of Claim 1 wherein said film is capable of adherence to a hard surface substrate at a temperature of between 300°C and 800°C.

25. (currently amended) A hard surface substrate to which a sol-gel film has been applied over at least a portion of the surface thereof at a temperature of between 300°C and 800°C, wherein the sol-gel film contains at least one silver-containing inorganic antimicrobial agent, and wherein said film-coated hard surface substrate exhibits a log kill rate for *Klebsiella pneumoniae* of at least 0.5, as measured under a modified plate contact method, at said portion to which said sol-gel film has been applied.